



A composition for increasing preservative capability and
promoting the growth of living organism and a preparing
method thereof

FIELD OF THE INVENTION

5 [1] The present invention relates to a composition promoting the growth of human body, animals and plants and increasing preservative capability of animals and plants.

[2] The present invention also relates to a producing method of the composition composed of natural substances
10 and compounds by mixing at almost the same ratio as that of inorganic substances in human, animals and plants.

[3] The producing method of the present invention may be used in the whole field of industries such as building materials, home appliances, a medical industry and a food
15 industry.

BACKGROUND

[4] Natural substances such as yellow soil and silicon dioxide mineral, and synthetic ceramic have been used in the whole field of industries such as medical instruments
20 using infrared-ray and home appliances.

[5] However, since the above-mentioned things is prepared by using the natural substances such as yellow soil and white soil as major components, content of a silicate (SiO_2) is high, whereas contents of inorganic
25 substances such as potassium, calcium, sodium, magnesium and iron are very low.

SUMMARY OF THE INVENTION

[6] It is an object of this invention to provide a composition activating physiological activity of human body, animals and plants at a maximum level.

5 [7] It is a further object of this invention to provide a producing method the composition.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

[8] Potassium, calcium, sodium, magnesium and iron are
10 major components of inorganic substances of human body, animals and plants. Thus, the composition of the present invention is prepared by mixing various components at almost the same ratio as that of inorganic components of animals and plants.

15 [9] The composition of the present invention contains kaoline(white soil) 30.0-40.0wt%, potassium sulfate 15.0-20.0wt%, sodium sulfate 13.0-17.0wt%, feldspar 12.0-16.0wt%, talc 12.0-16.0% and ferric oxide 0.5-1.5wt%. The composition is mixed by a compressed molding method with
20 water, dried and manufactured in random forms. The resulting composition becomes plastic at 1000-1300°C for its use in various forms.

[10] The composition of the present invention prepared by the above-mentioned composition has components
25 shown in the following Table 1.

<Table 1> Average ratio of components of composition

Components	Weight ratio (wt%)
Potassium (K)	19.06-23.29wt%
Calcium (Ca)	14.21-17.36wt%
Sodium (Na)	12.30-14.97wt%
Magnesium (Mg)	11.98-14.64wt%
Silicon (Si)	13.74-16.80wt%
Aluminum (Al)	12.21-15.13wt%
Iron (Fe)	3.48-4.26wt%
Titanium (Ti)	0.95-1.17wt%
Manganese (Mn)	0.28-0.40wt%
Zinc (Zn)	0.17-0.20wt%
Germanium (Ge)	0.07-0.09wt%
Selenium (Se)	0.03-0.04wt%
Other elements	1.36-1.67wt%

[11] The major components of the composition of the present invention are potassium, calcium, sodium and magnesium, which has similar distribution with inorganic substances of human body, animals and plants. In addition, the composition of the present invention has an affinity for silicon and aluminium abundantly contained in soil.

[12] Whereas, as shown in Table 2, general ceramic products contain large amounts of silicon and aluminium, and small amounts of potassium, calcium, sodium and magnesium.

<Table 2> Average ratio of components of general ceramic products

Components	Weight ratio (wt%)
Aluminium (Al)	35.36-43.22wt%
Silicon (Si)	31.33-38.30wt%
Potassium (K)	7.73-9.45wt%
Magnesium (Mg)	3.56-4.36wt%
Iron (Fe)	3.52-4.31wt%
Calcium (Ca)	3.40-4.16wt%
Sodium (Na)	2.79-3.63wt%
Titanium (Ti)	0.03-0.04wt%
Other elements	2.10-2.57wt%

[13] The ratio of components of general yellow soil ceramic is shown in Table 3.

<Table 3> Average ratio of components of general yellow soil ceramic

Components	Weight ratio (wt%)
Silicon dioxide (SiO_2)	64.08-79.42wt%
Aluminium oxide (Al_2O_3)	9.45-11.55wt%
Sodium oxide (Na_2O)	3.32-4.02wt%
Ferric oxide (Fe_2O_3)	2.93-3.58wt%
Potassium oxide (K_2O)	2.22-2.71wt%
Other elements	8.02-9.80wt%

5 [14] As shown in Table 3, the general yellow soil ceramic contains mostly silicon and aluminium as major components, and small amounts of potassium, calcium, sodium and magnesium which are associated with human body, animals and plants. Hereinafter, the present invention is described
10 in detail.

EXAMPLES

[15] Practical and presently preferred embodiments of the present invention are illustrative as shown in the
15 following Examples.

[16] However, it will be appreciated that those skilled in the art, on consideration of this disclosure, may make modifications and improvements within the spirit and scope of the present invention.

20

Example 1: Preparation of the composition

[17] The composition of the present invention contains the following components: i) Kaoline (white soil)

30-40wt%; ii) potassium sulfate 15.0-20.0wt%; iii) sodium sulfate 13.0-17.0wt%; iv) feldspar 12.0-16.0wt%; v) talc 12.0-16.0%; and vi) ferric oxide 0.5-1.5wt%.

[18] In the above composition, potassium sulfate and sodium sulfate may be replaced by the same amounts of potassium chloride and sodium chloride ions. However, because a moisture drying efficiency of sulfate salts are better than that of chloride salts, the present inventors selected potassium sulfate and sodium sulfate to increase the moisture drying efficiency.

[19] The composition was manufactured in form of minute powder of 100-150 mesh. After the composition was mixed by the compressed molding method or with 20-30wt% of water to mold in the fixed form, it was dried by hot wind at 40-80°C for 10-15 hours and heated 1000-1300°C for 2-3 hours to be plastic. The manufactured composition was prepared in various forms to be used for various industry.

[20] The composition of the present invention activated physiological activity of human body, animals and plants at a maximum level. In addition, Such activation by the composition of the present invention was superior to that by conventional ceramic products.

[21] Generally, infrared-ray irradiation of silicon is higher than that of potassium. Whereas, the composition of the present invention was excellent in biological effect on the living organisms.

**Experiment 1: Physiological reactivity of the composition
of the present invention and general ceramic products**

[22] The present inventors performed the physiological reactivity experiment of the composition and general ceramic products, and compared their physiological reactivities. The result was shown in Table 4.

<Table 4> The results of comparing the physiological reactivity.

Item	Refinement velocity of coffee taste	Refinement velocity of tobacco	deodorization of Refrigerator	Freshness of vegetables
Yellow ceramic	10 hours* (3 hours)	10 hours* (3 hours)	No effect	No effect
Medical ceramic	10 min* (20 sec)	5 min* (5 sec)	From 2 hours after starting	180% increase
Industrial ceramic	5 hours* (1 hour)	1 hour* (30 min)	From 5 hours after starting	130% increase
The composition of the present invention	30 sec* (10 sec)	20 sec* (2 sec)	From 30 min after starting	250% increase

<*:the experiment was performed at room temperature, ():

the experiment was performed at 50°C.

[23] The composition of the present invention was superior to the conventional ceramic products in exerting much more advantageous effects on the living organisms more rapidly.

[24] In addition, the composition was prepared in form of minute powder of 200-350 mesh and mixed with synthetic resin to the concentration of 5-30%. The resulting mixture can be used in various forms for industry.

[24] For example, after the composition of the

present invention was added to polyethylene film which has been used a vinyl house for cultivating plants, the present inventors cultivated the crops using the vinyl house made from the ployethylene film containing the composition of the present invention and the vinyl house made from general polyethylene film. The results was shown in Table 5.

<Table 5> The results of cultivating the crops

crop	Average yield		
	Polyethylene film	Polyethylene film containing the component	Comparison (increasing ratio)
Chinese cabbage	416 kg	499 kg	20% increase
Cucumber	422 kg	527 kg	25% increase
Tomato	575 kg	719 kg	25% increase
Red pepper	179 kg	250 kg	40% increase

(increase per 100 m² of cultivation areas)

[25] As shown in Table 5, when the synthetic resin containing the composition of the present invention was used, the yield of the crops was increased more about 20-40% than that when the general synthetic resin was used. Therefore, these results demonstrate that the composition of the present invention accelerates physiological activity of plants.

INDUSTRIAL APPLICABILITY

[26] The composition of the present invention, can maximize physiological activity of the human body, animals and plants. Thus, the composition of the present invention

can be used for industry and will cause the original changes in the field of industrial matters.

[27] In detail, for example, the composition of the present invention can be used all the industries including building materials and raw materials of various synthetic resins (especially, vinyl, plastic, etc.), various food containers, cosmetics and cosmetics containers, various medical instruments (especially, medical instruments using far infrared-ray), medicines and medicines containers, containers for cultivating various plants, deodorants and chemical products such as agricultural chemicals. Therefore, it is expected that the composition of the present invention will promote the welfare of human beings such as improvement of health and life of human.

[28] Those skilled in the art will appreciate that the conceptions and specific embodiments disclosed in the foregoing description may be readily utilized as a basis for modifying or designing other embodiments for carrying out the same purposes of the present invention. Those skilled in the art will also appreciate that such equivalent embodiments do not depart from the spirit and scope of the invention as set forth in the appended claims.